












## RAW MATERIALS

CODE	RAW MATERIAL	25g	50g	100g	250g	500g	1kg	5kg	Bag
<p><i>It is advisable to carry out glaze tests prior to mixing large amounts of glaze. As mineral properties can change from batch to batch, all materials should be sampled for their suitability prior to use. It is important to prove their effectiveness under the particular conditions that they are to be subjected to.</i></p>									
	Denotes Poisonous Materials	<p><b>WARNING:</b> When handling raw materials be sure to wear an Australian Standards Approved P3 (Toxic Protection Grade) Dust Mask, protective apparel, safety glasses and gloves. MSDS are available upon request.</p>							
ASLIP	Albury Slip (Albany equivalent)	-	-	-	-	-	20.00	-	-
AC100	Alumina Calcined 100	-	-	-	-	4.50	7.10	28.25	105.85 (25kg)
AH	Alumina Hydrate	-	-	-	-	4.85	8.00	31.95	119.75 (25kg)
BCFX	Ball Clay FX	-	-	-	-	-	2.35	9.25	34.60 (20kg)
BC	Barium Carbonate—Fine 	-	-	-	-	9.35	15.55	62.05	232.60 (25kg)
BW	Bentonite (Wyoming)	-	-	-	-	-	3.75	14.95	56.10 (25kg)
BAS	Bone Ash—Synthetic	-	-	-	9.05	15.50	25.80	103.20	387.00 (25kg)
B	Borax 	-	-	-	-	9.35	17.00	63.75	276.05 (25kg)
CO20	Calcite - Omya Carb 20 (Whiting)	-	-	-	-	-	2.25	5.45	20.40 (25kg)
CCC	Calcium Chloride Flakes	-	-	-	6.00	10.00	15.95	59.70	-
CCE2	China Clay—Eckalite 2 (Kaolin)	-	-	-	-	-	3.15	12.50	46.95 (25kg)
CHO	Chrome Oxide 	-	4.45	7.35	14.70	22.00	37.25	167.65	-
CMC	CMC Tylose—aids glaze adhesion	-	-	-	15.70	25.10	37.60	-	-
CC	Cobalt Carbonate	9.30	16.50	28.90	61.70	103.15	165.00	-	-
CO	Cobalt Oxide	11.90	19.75	34.70	73.65	120.95	178.60	-	-
COL	Colemanite	-	-	-	-	3.30	5.50	21.90	87.50 (25kg)
COC	Copper Carbonate 	-	-	11.80	25.25	42.10	67.35	252.40	-
COB	Copper Oxide—Black 	-	-	11.20	24.00	40.00	63.95	239.80	-
CS	Cornish Stone (Synthetic)	-	-	-	-	6.00	8.85	31.65	110.75 (25kg)
CF	Crack Filler (mends cracks in b/ware)	-	-	-	7.70	12.80	20.45	76.60	-
CRYO	Cryolite (Synthetic)	-	-	-	-	9.10	15.10	60.25	225.90 (25kg)
DL	Dolomite	-	-	-	-	-	4.20	16.75	56.90 (22.7kg)
EP	Egyptian Paste (Self glazing clay)	-	-	-	-	8.15	13.60	54.25	-
FP	Feldspar Potash	-	-	-	-	-	3.90	10.10	40.80 (25kg)
FS	Feldspar Soda	-	-	-	-	-	5.45	21.90	69.90 (25kg)
FC	Fire Clay	-	-	-	-	-	2.70	9.60	35.95 (25kg)
F	Fluorspar	-	-	-	-	-	3.80	16.85	64.25 (25kg)
GB	Gerstley Borate	-	-	-	-	7.45	12.35	49.35	168.00 (22.7kg)
GCFC	Grog (Calcined Flint Clay) 0.5mm to dust	-	-	-	-	-	3.50	13.90	52.05 (25kg)
GROG	Grog 0.7mm—1.3mm	-	-	-	-	-	6.60	23.95	95.00 (25kg)
IOB	Iron Oxide—Black	-	-	-	-	6.80	11.30	45.25	169.60 (25kg)

## RAW MATERIALS

CODE	RAW MATERIAL		50g	100g	250g	500g	1kg	5kg	Bag
IOL	Iron Oxide - Red (Local)		-	-	-	3.90	5.90	20.90	-
IOYO	Iron Oxide - Yellow Ochre Synthetic		-	-	5.35	9.20	15.30	61.20	229.50 (25kg)
CCE2	Kaolin - <i>refer to China Clay</i>								
LCF	Lithium Carbonate – Fine		-	19.75	42.25	73.25	123.90	-	-
MCH	Magnesium Carbonate - Heavy (Magnesite)		-	-	-	-	3.60	8.85	27.75 (25kg)
MCL	Magnesium Carbonate - Light		-	-	-	14.85	24.75	99.00	321.75 (25kg)
MD	Manganese Dioxide		-	-	-	5.45	7.20	30.90	-
MCK	Molochite - Calcined Kaolin		-	-	-	-	25.95	99.30	-
NS	Nepheline Syenite		-	-	-	-	6.55	25.45	76.60 (25kg)
NO	Nickel Oxide		15.05	26.35	56.25	93.65	149.85	-	-
PL	Petalite		-	-	-	13.40	22.30	89.10	334.15 (25kg)
PC	Potassium Carbonate (Pearl Ash)		-	-	-	4.80	8.00	36.35	161.80 (25kg)
PP	Potters Plaster		-	-	-	-	-	9.00	26.90 (20kg)
RF	Rutile Flour		-	-	15.70	26.90	44.80	179.10	-
SS	Silica Sand		-	-	-	-	2.70	9.70	36.30 (25kg)
S200	Silica 200		-	-	-	-	3.10	9.25	34.65 (25kg)
S350	Silica 350		-	-	-	-	3.40	9.90	37.15 (25kg)
SAD	Soda Ash - Dense		-	-	-	-	5.50	22.00	82.50 (25kg)
S	Spodumene		-	-	-	14.85	24.75	98.80	370.55 (25kg)
STC	Strontium Carbonate		-	7.30	15.75	27.05	45.05	179.95	-
T	Talc		-	-	-	-	3.85	15.20	56.95 (25kg)
TO	Tin Oxide		17.85	30.55	48.95	86.70	147.70	-	-
TD	Titanium Dioxide		-	-	9.05	15.30	25.50	101.90	382.00 (25kg)
W	Wollastonite		-	-	-	5.80	7.85	29.90	105.20 (25kg)
ZO	Zinc Oxide		-	-	-	9.15	15.20	60.80	228.00 (25kg)
ZF	Zircon Flour		-	-	-	5.20	8.25	35.10	-
ZS	Zircon Sand		-	-	-	3.20	5.30	18.50	112.20 (25kg)
ZSO	Zirconium Silicate Opacifier		-	-	7.30	11.40	19.00	76.00	312.00 (25kg)